

PRODUCT DESCRIPTION

TAL SUREPROOF MEMBRANE has been specifically designed and developed for all weather conditions and is used as a reinforcing membrane with TAL SUREPROOF waterproofing compound. The glass mesh in TAL SUREPROOF MEMBRANE provides exceptional dimensional stability to the membrane, improving the tensile strength in both longitudinal and lateral directions.

This, in turn, reinforces the TAL SUREPROOF waterproofing compound. TAL SUREPROOF MEMBRANE is not affected by ultra violet, does not rot or burn, is moisture, mild acid and mild alkali resistant.

APPLICATION

TAL SUREPROOF MEMBRANE must be used as reinforcement in all coving areas, internal corners and interfaces, over small static cracks in the substrate, around floor drains/wastes, and around roof penetrations.

Refer to TAL SUREPROOF data sheet and packaging instructions for application instructions in conjunction with TAL SUREPROOF.

TECHNICAL DATA

Product name	Sureproof Membrane
Mass	60g / m ²
Nominal thickness	0.40mm (over mesh)
Mesh type	2 x 2 construction 2/34/68
Nominal fibre diameter (microns)	16μ
Binder type	Acrylic
Binder content	12 – 18% by mass
Moisture content	3% maximum
Glass content	80% minimum
Nominal tensile strength	
- Long	400N / 50mm
- Lateral	400N / 50mm
Nominal pliability (strength after bending)	300N / 50mm

PACKAGING

TAL SUREPROOF MEMBRANE is available in 200mm x 10m and 1m x 100m rolls.

STORAGE

Must be stored in dry internal conditions between 10°C and 30°C and out of direct sunlight.

WARNING:

DO NOT INGEST. USE ONLY AS DIRECTED. DISPOSE OF THIS PRODUCT IN ACCORDANCE WITH LOCAL REGULATIONS. CONTACT TAL FOR FURTHER HEALTH AND SAFETY INFORMATION.